

Efecte primari	B*C*D	A*C*D	A*B*D	C*D	D*B	A*D	D	
Efecte bàsic	A	B	C	A*B	A*C	B*C	A*B*C	
Buidat caixaera	Estratègia	Diàmetre	Recobriment				Velocitat tall	Rugositat
1	1	1	1	2	2	2	1	0,353
2	1	1	2	2	1	1	2	0,932
3	1	2	1	1	2	1	2	1,234
4	1	2	2	1	1	2	1	0,496
5	2	1	1	1	1	2	2	1,453
6	2	1	2	1	2	1	1	0,815
7	2	2	1	2	1	1	1	1,430
8	2	2	2	2	2	2	2	2,711
Mitjana 2	1,602	1,467	1,238	1,356	1,278	1,253	1,582	
Mitjana 1	0,754	0,888	1,117	0,999	1,078	1,103	0,774	
Efecte rugositat	0,848	0,579	0,121	0,357	0,201	0,151	0,809	

Intersecció dels factors

a1b1	1,3	c1d1	1,8	Constant	3,5
a2b1	2,3	c2d1	1,3	Recorregut rug	0,195
a1b2	1,7	c1d2	2,7	Error experimer	0,6816
a2b2	4,1	c2d2	3,6		
a1c1	1,6	b1d1	1,2		
a2c1	2,9	b2d1	1,9		
a1c2	1,4	b1d2	2,4		
a2c2	3,5	b2d2	3,9		

