

Efecte primari	B*C*D	A*C*D	A*B*D	C*D	D*B	A*D	D	
Efecte bàsic	A	B	C	A*B	A*C	B*C	A*B*C	
Caixera	Estratègia	Diàmetre	Recobriments				Velocitat tall	Rugositat
1	1	1	1	2	2	2	1	1,43125
2	1	1	2	2	1	1	2	1,49025
3	1	2	1	1	2	1	2	1,1065
4	1	2	2	1	1	2	1	0,99725
5	2	1	1	1	1	2	2	1,6205
6	2	1	2	1	2	1	1	1,10475
7	2	2	1	2	1	1	1	1,49525
8	2	2	2	2	2	2	2	3,143
Mitjana 2	1,841	1,686	1,684	1,890	1,696	1,798	1,840	
Mitjana 1	1,256	1,412	1,413	1,207	1,401	1,299	1,257	
Efecte rug.	0,585	0,274	0,270	0,683	0,296	0,499	0,583	

Interseccions dels factors

a1b1	2,922	c1d1	2,927	Constant	3,5
a2b1	2,725	c2d1	2,102	Recoregut rugositat	0,345
a1b2	2,104	c1d2	2,727	Error experimental	1,206
a2b2	4,638	c2d2	4,633		
a1d1	2,429	b1c1	3,052		
a2d1	2,600	b2c1	2,602		
a1d2	2,597	b1c2	2,595		
a2d2	4,764	b2c2	4,140		

