


Gd Polvores 400C 800C 60min



Gd Polvores 400C 800C 60min - File: Gd Polvores 400C 800C 60min.raw - Type: 2Th/Th locked - Start: 10.000 ° - End: 80.000 ° - Step: 0.050 ° - Step time: 48. s - Temp.: 25 °C (Room) - Time Started: 1406616 832 s - 2-Theta: 10.0
Operations: Background 1.000,1.000 | Import

41-0173 (*) - Barium Copper Gadolinium Oxide - GdBa₂Cu₃O₇ - Y: 75.34 % - d x by: 1. - WL: 1.5406 - Orthorhombic - a 3.89470 - b 3.83500 - c 11.69920 - alpha 90.000 - beta 90.000 - gamma 90.000 - Primitive - Pmmm (47) - 1 -

45-1471 (*) - Witherite, syn - BaCO₃ - Y: 72.92 % - d x by: 1. - WL: 1.5406 - Orthorhombic - a 6.43300 - b 5.31480 - c 8.90360 - alpha 90.000 - beta 90.000 - gamma 90.000 - Primitive - Pnma (62) - 4 - 304.415 - I/Ic PDF 3.4 -