


YBCO 350C Jaume



☒ YBCO 350C Jaume - File: YBCO 350C Jaume.raw - Type: 2Th/Th locked - Start: 10.000 ° - End: 80.000 ° - Step: 0.050 ° - Step time: 2. s - Temp.: 25 °C (Room) - Time Started: 1404118912 s - 2-Theta: 10.000 ° - Theta: 5.000 ° - C
 Operations: Background 1.000,1.000 | Import
☒ 41-1105 (*) - Yttrium Oxide - Y₂O₃ - Y: 60.42 % - d x by: 1. - WL: 1.5406 - Cubic - a 10.60410 - b 10.60410 - c 10.60410 - alpha 90.000 - beta 90.000 - gamma 90.000 - Body-centred - Ia3 (206) - 16 - 1192.40 - I/Ic PDF 9.1 - S-Q 16
☒ 45-1471 (*) - Witherite, syn - BaCO₃ - Y: 83.50 % - d x by: 1. - WL: 1.5406 - Orthorhombic - a 6.43300 - b 5.31480 - c 8.90360 - alpha 90.000 - beta 90.000 - gamma 90.000 - Primitive - Pnma (62) - 4 - 304.415 - I/Ic PDF 3.4 - S-Q 6
☒ 89-2838 (C) - Copper - Cu - Y: 81.25 % - d x by: 1. - WL: 1.5406 - Cubic - a 3.61505 - b 3.61505 - c 3.61505 - alpha 90.000 - beta 90.000 - gamma 90.000 - Face-centred - Fm-3m (225) - 4 - 47.2436 - I/Ic PDF 8.9 - S-Q 22.7 % -